

	Method	Unit	HMPE 500	UHMPE 1000
<b>Colour</b>	-	-	White, Black, Color	White, Black, Color
<b>Specific Gravity</b>	ISO-1183-1	g/cm3	0,96	0,93
<b>Water absorption</b>	ISO 62 24/96 hr *	%	-	-
	Saturation in air 23°C 50% RH	%	-	-
	Saturation in water 23°C	%	-	-
<b>Coefficient of thermal expansion</b>	ISO 11357 **	m(m.K)	180*10-6	180*10-6
<b>Thermal conductivity @ 23°C</b>	-	W(K.m)	0,4	0,4
<b>Max Service temperature 5000 h</b>	-	°C	80	80
<b>Min. Service temperature</b>	-	°C	-100	-250
<b>Tensile strength</b>	ISO 527	Mpa	27	20
<b>Tensile strain at yield</b>	ISO 527	%	-	-
<b>Tensile module of elasticity</b>	ISO 527	MPa	1200	680
<b>Charpy impact test notched</b>	ISO 179-1	kJ/m2	NB	NB
<b>Shore hardness</b>	ISO 2039-2	-	65D	63D
<b>Electric Strength</b>	IEC 60243-1	kV/mm	45	45
<b>Volume resistivity</b>	IEC 60093	Ohm.cm	10exp14	10exp14

\* immersion in water of 23°C

\*\* average value between 23 and 60 °C

The following information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our advice concerning safety does not release you from the obligation to determine the safety measures designed for your production environment, that we may not be able to anticipate, to check abilities and to inform the people who will use, handle or be in contact with these products.

Subject to change without notice



Herikon B.V.  
T +31 (0)546 486 486  
F +31 (0)546 486 480  
E info@herikon.nl

Main Office  
Edisonstraat 11  
7601 PS Almelo  
The Netherlands

IBAN NL39 RABO 0141091673  
BIC RABONL2U  
KvK 06044166  
BTW NL006974491B01